



Blanca

NR/SBR-rubber



Material
NR/SBR

Color
White (blank)

Density (gr/cm³)
±1,3

Hardness (°Shore)
65 ±5

Pressure max. (bar)
10

Temperature limit (°C)
-45°C to max +80°C

Application
Blanca is odourless and tasteless whereby it is best suited in the food industry.

Approvals and certificates

- EC 1935/2004
- FDA

Table 1: Technical data*

Property	Norm	Value	Unit
Max. surface pressure σ_{v_0}		10	MPa
Minimum temperature		-45	°C
Maximum temperature		+80	°C
Hardness	ASTM 2240	65	Shore A
Elongation at break	ISO 37	600	%
Tensile strength	ISO 37	10	MPa
Compression - 24 hr at 70 °C	ISO 815	35	%
Density		1,3	g/cm ³

* Depending on temperature en construction.

Table 2: Supply programme*

Thickness (mm)	Inserts	Width (mm)	Length (mm)	Part no.
1	-	1400	20	10017100
2	-	1400	15	10017101
3	-	1400	10	10017102
4	-	1400	10	10017103
5	-	1400	10	10017104
6	-	1400	5	10017105
8	-	1400	5	10017106
10	-	1400	5	10017107

* Deviating thickness available upon request. Gaskets according to drawings can easily and quickly be manufactured.

Disclaimer: The content of this document has been composed with the utmost care. However, it is possible that certain information changes over time, becomes inaccurate or in-complete. ERIKS does not guarantee that the information provided on this document is up to date, accurate and complete; the information provided is not intended to be advice. ERIKS shall never be liable for damage resulting from the use of the information provided.

For more information, quotations or orders: Phone +31 (0)72 514 15 14 or E-mail info@eriks.nl